HLW Catalytic Oxidizer/Reducer Mechanical Data Sheet

Data Sheet No. 24590-HLW-MKD-HOP-P0019

Rev.

Component No.

24590-HLW-MB-HOP-SCO-00002

Waste Treatment Plant 1 of RPP-WTP System Description 24590

HOP

HLW

2

Category III

bystem Description	Thermal Catalytic Oxidizen Scientific Catalytic Reduction	_
Reference Doc	Specification 24590-WTP-3PS-MBTV-TP001	
1	PDS 24590-HLW-MKD-HOP-00011	_
Associated Dwgs	24590-HLW-M5-V17T-P0004	_
1	24590-HLW-M6-HOP-P0008	_

PROCESS DATA (Buyer)

Offgas Inlet Conditions:

Project No. System No.

Building

Quality Level

Seismic Criteria

		Normal	Maximum	Design
Vol. Flow	(acfm)	2250	3062	2000 scfm
Temperature	(°F)	330	330	(note 1)
Pressure	(in wg)	-32.4	-50.9	± 80
Allowable	Allowable Diff Pressu		(in. wg)	10

Process Data Notes.

- Design Temperature for the Thermal Catalytic Oxidizer/Selective Catalytic Reduction internals and vessel shall be determined by the Seller based on the thermodynamic activities in the equipment
- 2. Minimum NOx concentration ranges to 0 lb/hr.

Primary Offgas Inlet Composition:

		Nominal	Maximum
N ₂	(By Volume)	69.9%	65 8%
O ₂	(By Volume)	18.7%	17 6%
H ₂ O	(By Volume)	10.1%	14 9%
CO ₂	(By Volume)	0.36%	0.55%
Ar	(By Volume)	0.84%	0 79%
NO _X (note 2)	(lb/hr)	4.4	26
СО	(lb/hr)	0.25	0 50
SO ₂	(g/hr)	0 30	0 25
Hg	(g/hr)	4.6E-04	2 4E-02
HCI	(g/hr)	1.4E-05	9.8E-05
HF	(g/hr)	4.4E-04	4 2E-03
l ₂	(g/hr)	7.4E-11	5 4E-08
Total of As, Cr, C	Cu,		
Fe, Nı, Pb, Sb, Si,	(g/hr)	1.6E-11	1 IE-10
Sn, Zn			
Organics	(lb/hr)	< 0.5	0 to 4

Ammonía Supply:

		Nominal	Maximum
Temperature	(°F)	77	125
Specific Gravity (vapor)	(lb/lb air SC)	6.00	12 8
Viscosity	(μP)	100	137
Internal Pressure	(psia)	145	314
Solids Content	(wt.%)	0%	0%

Note:

Buyer will supply anhydrous ammonia at Seller's specified flowrate to meet design conditions Seller is responsible for flow control of anhydrous ammonia to meet performance requirements. Ammonia vaporizer assure nominial conditions.

Performance Requirements

- The destruction removal efficiency (DRE) for volatile organic compounds (VOCs) and semi-volatile compounds (SVOCs) shall be greater than or equal to 95%. The Principal Organic Dangerous Constituents (PODCs) to be used in HLW performance testing are naphthalene (CAS 91-20-3) and 2-propene-1-01 (CAS 107-18-6). A DRE greater than 95% is preferred
- The NO_x Selective Catalytic Reduction (SCR) unit shall perform with a reduction efficiency of 95%.

Dioxin and furan emissions at the outlet of the Thermal Catalytic Oxidizer/Reducers shall meet the MACT criteria of 0.2 ng/m³ TEQ (Toxic Equivalent).

Note: Please note that source, special nuclear and byproduct materials, as defined in the Atomic Energy Act of 1954 (AEA), are regulated at the U.S. Department of Energy (DOE) facilities exclusively by DOE acting pursuant to its AEA authority. DOE asserts, that pursuant to the AEA, it has sole and exclusive responsibility and authority to regulate source, special nuclear, and byproduct materials at DOE-owned nuclear facilities. Information contained herein on radionuclides is provided for process description purposes only.

Contents of this document are Dangerous Waste Permit affecting.

This Bound Document Contains a total of 4 sheets



EXPIRES 12/10/64

		1			100	
0	Issued for Permitting Use	145-	Lee	CHA	Work-	9/29/0
Rev	Reason for revision	Ву	Check	Review	Appr ay d	Date

				HLW	Catalytic ()xidizer/l	Reducer		
								Data Sheet No.	Rev
						eet 2	of 4	24590-HLW-MKD-HOP-P0019	0
				MEC	HANICAL	. DATA (Buyer)		
Construction Da									
Process Equipment								(L x W x H):	(1 6
Section			x 6 ft				ns with dil		
Overal	1	25 x 5 x						dilution fans $8' \times 5' \times 2000$	
Operating Weight	(1	7.1	lbf	0	•	ating Weig		9000	lbf
Shipping Dimensio	ns (L x w x	н) .		ft	•		nsions (L x	W x H) 12' x 5' x 8000	
Shipping Weight				lbf	Suib	ping Weigl	ıt	8000	lbf
Thermal Analysis	Data:								
Room Temperature	:			83 °F	Conc	crete Slab I	Base Thickn	ess <u>6</u>	Ft
Earth Temperature	Under Base			70 °F	Ther	mal Condu	ctivity of C	oncrete Slab $K = 1.8$	W / m / K
Maximum Heat Lo	SS			15 Kw					
Thermal Cycling Fr	equency.	For	lecian nurn	OCEC 1158 9	thermal cycle	frequency	of once eve	ery two (2) months	
incinial Cycling Fi	equency		·	e plant (40	•	nequency	or once eve	ay two (2) months	
				c piant (40	jearsj.				
Process Pipe and l	_		Data:						
Pipe Class		11V					sing Materi		
Pipe Material		16 L SS				Ratı	-	ASME B16.5	
Flange Material	-	16 L SS					Piping Size		
Flange Rating		150 RF E		D16.30		Out	let Piping S	Size <u>16</u> inches	
Gasket Material	31	o SS Spira	al-Wound /	B16.20					
Ammonia Piping:									
Pipe Class		530J				Rati	_	ASME B16.5	
Pipe Material	****	<u>04 L</u> SS					Piping Size		
Flange Material		04 L SS					e Material		
Flange Rating		300 RF E				Val	e Trim	TRIM 12, API 600	
Gasket Material	31	6 SS Spira	al-Wound /	Graphite Fi					
				N	ozzle Load	ings (Buy	er)		
Inlet:							•		
Load Case	Fa	Fb	Fc	Ma	Mb	Mc	l -		···-
	(lb)	(lb)	(lb)	(ft-lb)	(ft-lb)	(ft-lb)			≠ ^N
Weight	400	-500	400	1000	3000	-1000			F _b
Thermal (+)	200	1000	200	2000	2000	2000			
Thermal (-)	-4400	-1000	-1000	-7000	-15000	-25000			
Seismic (+)	3500	3500	3500	11000	18000	18000			F,
Seismic (-)	-3500	-3500	-3500	-11000	-18000	-18000			
Normal (+)	600	500	600	3000	5000	1000		a = axial	
Normal (-)	-4000	-1500	-600	-6000	-12000	-26000		b = verts c = by n	cal up ght hand rule
Occasional (+)	4100	4000	4100	14000	23000	19000			
Occasional (-)	-7500	-5000	-4100	-17000	-30000	-44000			
Nozzle move	ements at	°F:	Δa =	, Δb =	, and ∆c	-	(nominal)		
			Δa =	, Δb =	, and ∆c	=	(design)		
Outlet:									
Load Case	Fa	Fb	Fc	Ma	Mb	Mc		F.	N
	(lb)	(lb)	(lb)	(ft-lb)	(ft-lb)	(ft-lb)		↑F.	
Weight	-1700	1000	2000	-200	-500	500			
Thermal (+)	2000	1000	2000	100 -20000	-2000	1000		F _b	
Thermal (-) Seismic (+)	-1300 4200	-2000 6600	-2000 6600	9500	75000	-16000 75000		a = axial to nozzle b = along heat exchai c = by right hand rule	nger axis
	-4200	-6600	-6600	-9500 -9500	-75000 -75000	-75000			
Seismic (-)		-0000	-0000	-9300	-75000	-/3000			
Normal (+)	300	1400	2400	800	12500	1500	/	/ \	
Normal (-)	-3000	-1600	-1600	-20200	-2500	-15500		()	
Occasional (+)	4500	8000	9000	10300	87500	76500		\ /	
Occasional (-)	-7200	-8200	-8200	-29700	-77500	-90500			
Nozzle move	ements at	°F·			, and ∆c		(nominal)		
				, Δb =	, and ∆c	=	(design)		
Notes: 1.	Normal = '	Weight +	Thermal						
	Occasiona			_					

	HLW Catalytic Oxidizer/Reducer		
		Data Sheet No.	Rev
	Sheet 3 of 4	24590-HLW-MKD-HOP-P0019	0
	SYSTEM PERFORMANCE (Seller)	****	
Volatile Organic DRE 95 %	Semi-Volatile Organic DF		
NO _X Reduction 95 %	Ammonia consumption, n		
NO _X emissions, max 58 ppm @ 79			
Ammonia slip, max 20 ppm @ 79		1.0 in-WG Pressure	1.0 in-WG
Ammonia/NO _x molar injection ratio		9.3 lb/hr (max) Flow	200 scfm
		100 °F	
·	VOC 2 yrs (EST) NO_X 2	yrs (EST.)	
Recommended Catalyst replacement schedule	Test at 1 year to determine activity level. Re	placement schedule could be	
	2-4 year intervals		
	COMPONENTS (Seller)		
Catalyst:	Organic	NO _x	
Manufacturer	Engelhard (VOCAT 360 PFC)	Haldor Topsoe	
Number of reactors	9	50	
Residence time, sec	0.15	1.20	
Arrangement	2 blocks x 4.5	3.5 high x 3 wide	e
Catalyst vol. per reactor ft ³	7	76 62	
Туре	Precious metal - platinum	Vanadium/Titaniu	ım
Material: base/substrate	ceramic - cordierite	ceramic - honeyco	mb
Number of layers per reactor	2	5	
Thickness of layer, in	4 3	10 0	
Spacing between layer, in	0 125	0 125	
Space for additional layer, in	8.5	none	
Is dummy layer provided	Yes	No	
Flow passage, in. x in	0.066" x 0.066"	0.125" x 0.125"	
Face velocity thru reactor, fpm	486	292	
Max allowable temp, °F	1300	1100	
Min. allowable temp, °F	700	550	
Module Dimensions, (L x W x D)	12.5" x 12.5" x 8.5"	18" x 18" x 10"	
Module weight, lb	40	45	
Total weight per reactor, lb	360	2425	
Housing:			
Material/Thickness, in	3/8" plate 316L SS	3/8" plate 316L SS	5
Number of Section	2	1	
Weight of Heaviest Section, lb	30,000	20,000	
Insulation Lining	Ceramic fiber block	Ceramic fiber bloc	
Material/Thickness, in	7" thick 8 lbs density	7" thick 8 lbs densi	
Thermal Cond, Btu-in/hr ft2 °F	40 btu-in/hr ft ^{2 o} F	40 btu-ın/hr fl ^{2 o} F	
Method of Attachment	Weld stud w/ your attachmt	Weld stud w/ your atta	chmt
Design pressure, psig	3.5	3 5	
Operating pressure, psig Design temperature, 'F	15	15	
	1300	1300	
Ducting Natural Vision on the Control of the Contro	2/98 plate 2141 SS	7/9# plate 2141 S6	2
Material/Thickness, in	3/8" plate 316L SS 3' tall x 2' wide	3/8" plate 316L SS 3' tall x 2' wide	<u> </u>
Cross Section, ft x ft Duct Velocity, fpm	700	700	
Electric Heater	,00	1 ,	
Manufacturer	u.	/atlow	
Туре		Elements - Watrod	
Number of Heat Zone		ing elements	
Watt Density, W/in ²	37 neuti	12	
Power, kW		155	
Voltage/Current rating		186.5 amps 1	

				Data Sheet No.	Rev.
	Sheet 4	of	4	24590-HLW-MKD-HOP-P0019	0
ecuperative Heat Exchanger					
Manufacturer		Ex	othen	mıc Eclipse	
Туре			Pla	te type	
Material			31	6L SS	
Ht transfer coefficient, Btu/hr ft ² °F				5.76	
Heat exchange area, ft ²			2	,179	
ΔT (LMTD)				194	
Heat Eexchanger duty, Btu/hr			2,4	39,000	
mmonia Injection Manifold					
Type/Arrangement			S	pider	
Feed Inlet Dia in	1/2" dia.				
Supply Pressure/Temp (psi/°F)		1	psig	@ 100%	
Material/Quantity			31	6L SS	
No. of nozzle bar per manifold			6 n	ozzles	
No. of nozzles per bar				6	
Spacing between nozzles, in		_	3	3.5"	
Nozzle opening diameter, in			(0.5"	
Weight					
Shipping (Heaviest), lb	30,000 lbs			15,000 lbs	
Installed, ib	30,000 lbs			15,000 lbs	
Shipping dimension (L x W x H), in	12 5' x 5' x 6'			12 5' x 5' x 6'	

Notes

NOTES:

- 1. Deleted
- 2. Deleted
- 3. Seller's data is rounded and based on preliminary engineering design.
- 4. Sub component tag numbers:

24590-HLW-HOP-HX-00001

24590-HLW-HOP-HTR-00001 24590-HLW-HOP-SCO-00001 24590-HLW-HOP-SCR-00001